(54) Title: BIPOLAR PLATES FOR ELECTROCHEMICAL CELLS

(57) Abstract

A bipolar separator plate for two electrochemical cells connected in series, the plate having two layers of a porous electronically conductive material having positioned therebetween a solid layer of a polymeric material having dispersed therein at least 1 percent by weight of a conductive filler, wherein the plate has an area resistivity of less than 1 ohm-cm^2, and wherein the solid layer has a permeability of less than 50 μDarcy (μD).

BIPOLAR PLATES FOR ELECTROCHEMICAL CELLS

This invention relates to electrochemical cells, and more particularly to components of such cells that have low permeability and are electronically conductive.

5   Electrochemical cells typically contain separator plates which are relatively impermeable to gases or liquid contained in the cell. Such plates are usually part of a gas or liquid distribution assembly. In fuel cells, for example, the separator plate is typically a graphite plate which has gas distribution channels machined into one of its surfaces. However, such plates are expensive to produce. U.S. Patent No. 4,505,992 discloses a

10   laminate for use as part of a fuel cell assembly which comprises having a layer of a sealant material sandwiched between two porous carbon plates. However, the permeability and resistivity characteristics of such a composite may be less than desirable for certain applications.

Figure 1 illustrates a bipolar plate.

15   Figure 2 illustrates a bipolar plate having built-in cooling channels.

Figure 3 illustrates an assembly of components of a bipolar plate with cooling channels, prior to molding the assembly.

Figure 4 is an exploded schematic diagram of stack based on porous flow fields and containing the bipolar plate material of the present invention.

20   Figure 5 shows selected components of a fuel cell stack, including the (a) air delivery layer; (b) air flow field; (c) hydrogen delivery layer; and (d) hydrogen flow field.

In one aspect, this invention is a bipolar separator plate for two electrochemical cells connected in series, the plate comprising two layers of a porous electronically-conductive material having positioned therebetween a solid layer of a polymeric material having

25   dispersed therein at least 1 percent by weight of a conductive filler, wherein the plate has an area resistivity of less than 1 ohm-cm^2, and wherein the solid layer has a permeability of less than 50 μDarcy (μD).

In another aspect, this invention is an electrochemical device having at least two electrochemical cells connected in series, each cell containing a gas or liquid material which

is separated from a different gas or liquid material in an adjacent cell by two porous layers of electronically-conductive material having positioned therebetween a solid layer of a polymeric material having dispersed therein at least 1 percent by weight of a conductive filler, wherein the plate has an area resistivity of less than 1 ohm-cm^2, and wherein the solid

5   layer has a permeability of less than 50 μD.

It has been discovered that the bipolar plate of the invention has desirable permeability, resistivity, and structural integrity characteristics for use in an electrochemical cell, particularly for cells in which the reactants on either side of the plate are pressurized. These and other advantages of the invention will be apparent from the description which

10   follows.

Examples of suitable porous electronically-conductive materials include carbon paper, graphite paper, carbon felts, or other carbon-based composites, porous metal materials such as sintered metals, metal meshes, and metal screens, and solid, porous, electronically conductive polymers having a thickness of at least 1 mil. The optimum

15   thickness for the material will depend on the application, as well as the desired permeability and conductivity. Preferably, the material has a porosity of at least 20 percent, more preferably at least 40, most preferably at least 60 percent; but is preferably no greater than 90 percent, more preferably no greater than 85 percent, most preferably no greater than 80 percent.

20   Suitable polymeric materials which contain the conductive filler include any thermoplastic or thermosetting polymer which is a solid at ambient conditions (about 23°C), stable under the operating conditions of the electrochemical cell, and can be mixed with a conductive filler and processed into the shape of a separator plate for use with electrochemical cells. Examples of such include polyolefins, polystyrenes, polyepoxides,

25   polyurethanes (including Isoplast™ and Pellethane™ polyurethane resins, available from The Dow Chemical Company), polytetrafluoroethylenes, polyacrylates, polyethylene terephthalate, polyvinylchloride, polyvinylidene fluoride, vinyl ester resins (available from The Dow Chemical Company as Derakane™ resins), acrylonitrile-butadiene-styrene copolymers, polyamides, polyesters, linear polyimides, liquid crystal polymers, as well as

30   blends and copolymers thereof. Preferably, the polymer is polypropylene, syndiotactic

polystyrene, Isoplast™ polyurethane resin, polyvinylidene fluoride, a vinyl ester resin, or polytetrafluoroethylene.

Suitable conductive fillers include electronically-conductive grades of carbon black, carbon fibers, graphite, metal fibers and particles, and particles of intrinsically-conductive

5   polymers. Suitable carbon fibers include those having a length of about 0.25 inch and a diameter of about 7 μm, as well as agglomerates of fibers having an aspect ratio of at least 5 and a diameter in the range of 3.5 to 70 nm as described, for example, in WO 91/03057. Suitable graphite particles have a size in the range of 20 to 500 nm and a surface area in the range of 1 to 100 m²/g. Examples of suitable carbon blacks include particles of carbon

10   having an average primary particle diameter of less than 125 nm, more preferably of less than 60 nm. The carbon black is preferably utilized as an aggregate or agglomerate of primary particles, the aggregate or agglomerate typically having a size of 5 to 10 times the primary particle size. Larger agglomerates, beads, or pellets of carbon particles may also be utilized as a starting material in the preparation of the composition, so long as they

15   disperse during the preparation or processing of the composition sufficiently to reach an average size in the cured composition of less than 10 microns, more preferably less than 5 microns, and most preferably less than 1.25 microns. Preferably, the conductive filler is a carbon fiber having an aspect ratio of at least 5, more preferably at least 50, most preferably at least 100. However, the optimum aspect ratio of the fiber will depend on the mean pore

20   size of the porous electronically-conductive material, with longer fibers being more suitable for use with larger mean pore size materials.

The conductive filler is preferably employed in an amount, based on the weight of the polymeric material, of at least 1 percent, more preferably at least 10 percent, most preferably at least 20 percent; but preferably no greater than 90 percent, more preferably no

25   greater than 70 percent.

The bipolar plate may be made by any suitable process, but is preferably prepared by injection or compression molding a mixture of a thermoplastic polymer and a conductive carbon into the desired shape and size, and then combining the porous conductive layers with the molded layer by compression molding a multilayer composite of the molded layer

30   positioned between two layers of the porous conductive material. Alternatively, sheets of a filled thermoplastic material may be compression molded between layers of the porous

conductive material. In a third embodiment, a filled thermoplastic material may be injected between two layers of the porous conductive material in a mold, and then the resulting composite is compression molded.

The pressure and temperature of the process should be high enough to ensure
5   good electrical contact between the conductive layer and the porous layers, and to increase the density of the solid layer and/or the electronically-conductive material, if necessary to achieve the desired permeability characteristics and/or better conductivity. Preferably, the pressure and temperature is sufficient to cause a portion of the solid conductive layer to migrate into the pores of the porous layer in order to achieve better electrical contact
10   between the layers. As the polymer portion of the layer migrates into the porous material, the conductive carbon tends to stay between the two porous layers and the concentration of conductive carbon in the middle layer increases accordingly, thereby increasing the conductivity of that layer. Although the degree of compaction of the composite may vary depending on the materials (such as, for example, the carbon paper thickness and porosity)
15   and the performance requirements for use in a particular type of electrochemical cell, the composite is preferably compressed under conditions sufficient to reduce its volume by 5 to 80 percent. Figure 1 shows a bipolar plate prepared by a compression molding process, having two layers of porous carbon paper (1) and a layer of a polymer containing a conductive filler (2). During the molding process, a portion of the polymer migrated into the
20   porous carbon paper (3).

If a thermosetting polymer is used, the bipolar plate may be prepared by injecting the reactive monomeric components of a multi-part reactive thermosetting mixture (containing conductive filler) between two layers of the porous conductive material in a mold. Alternatively, a latent-curable thermosetting polymer may be used in processes similar to
25   those employed with thermoplastic polymers. The bipolar plate containing the uncured polymer may then be subjected to reaction conditions which cause the polymer to crosslink or cure.

The optimum thickness of the bipolar plate will depend on the types of electrochemical cell in which it is employed. For fuel cells, the thickness is preferably at
30   least about 2 mils, more preferably at least 5 mils, most preferably at least 10 mils; but is

preferably no greater than 200 mils, more preferably no greater than 100 mils, most
preferably no greater than 75 mils.

Permeability

The permeability of the solid layer is less than 50 microdarcys (μD). Preferably, the
5   permeability is less than 20 μD and is more preferably less than 10 μD. The permeability of
the layer may be measured according to the following method: The solid material to be
tested is mounted in a simple pressure cell equipped with rubber gaskets that prevent gas
flow around the sample as well as to the outside of the cell. Pressurized air at 30 psig is
supplied to one face of the sample while the air flow rate at atmospheric pressure is
10   measured using a soap bubble or other flow rate measuring device. The permeability of the
solid material is calculated from the pressure and flow data using the Darcy equation for a
compressible fluid:

$$K = \frac{2\,\mu\,L\,Q_a\,P_a}{A\,(P_b^2 - P_a^2)}$$

where K is the permeability in cm^2 (K can also be expressed in Darcys; 1 Darcy =
15   0.99x10^{-8} cm^2), μ is the viscosity of the fluid at the measurement temperature in pascal
seconds, L is the length of the flow path in cm (the thickness of the solid material in this
case), Q_a is the flow rate at the outlet in cm^3/s, P_a is the pressure at the outlet in pascals, A
is the area in cm^2, and P_b is the pressure at the inlet in pascals.

If the electrochemical cell is a fuel cell, the bipolar plate preferably has a "leak rate"
20   of no greater than 3 cm/min, more preferably no greater than 1 cm/min, and most preferably
no greater than 0.3 cm/min. The procedure for measuring the leak rate is as follows:
mount the sample in a pressure cell and apply 30 psig air to one side of the sample and
measure the air flow rate (at 0 psig) out the other side. The leak rate is the flow rate (in
cm^3/min) divided by the area (in cm^2) of the bipolar plate.

Resistivity
25

The area resistivity of the bipolar plate is preferably less than 0.1 Ω-cm^2, more
preferably less than 0.01 Ω-cm^2, and most preferably less than 0.003 Ω-cm^2. The area

resistivity may be measured and calculated as follows: Resistance is measured by clamping a 4 cm² bipolar plate between two (4 cm²) brass plates which serve as direct current (250 mA) carrying electrodes. The voltage across the thickness of the sample is measured via screws mounted in and electrically isolated from each brass plate. The

5   resistance is then calculated by diving the measured voltage by the current. The Area Resistivity = Rs, where R = resistance (Ω) and s = area of bipolar plate being measured (i.e., area of brass plate) (cm²).

<u>Cooling Channels</u>

In another embodiment of the invention, cooling channels may be built into the

10   bipolar plate, which are useful if the electrochemical cell generates heat and optimum performance is achieved if the device temperature is kept low. For example, during its regular operation an individual fuel cell or stack will generate heat. Built in cooling channels in the bipolar plates will help manage this heat by convection or by circulating cooling fluid through this channels (see Figure 2 for illustration).

15   For fuel cell stacks of less than 1 kilowatt, it is expected that air driven by a fan through straight cooling channels would be sufficient. For higher wattage stacks, the cooling channels may need to contain a different heat-exchange fluid. Cooling channels may be fabricated using a small diameter (such as 1/16 inch) polytetrafluoroethylene tubing or small gauge (such as 18 gauge) stainless steel tubing. Further, the addition of cooling

20   channels may require the fabrication of thicker bipolar plates. After the fabrication of the bipolar plate with cooling channels, the tubing may be extracted from the bipolar plate, leaving built-in length-wise through channels in the plate, or may be left in place.

A preferred fabrication process is as follows: (1) Two carbon-filled thermoplastic plates are prepared; (2) A number of conduits are cut to lengths greater than the width of

25   the desired bipolar plate; (3) Two carbon paper pieces are cut to fit the width and length of the mold chase; (4) Inside the chase, arrange the different components in the following order (as illustrated in Figure 3): Carbon paper layer, Carbon-reinforced thermoplastic plate, Conduits at regular parallel intervals covering the desired cooling area (To keep conduits in place, location plates which do not extend into the interior of the assembly and

30   do not become a part of it may be needed), Carbon-reinforced thermoplastic plate, Carbon

paper layer; (5) Using a regular fabrication cycle, mold the arrangement prepared in step (4); and (6) Retrieve bipolar plate with cooling channels.

<u>Bipolar Plates with Cooling Flow Fields</u>

In another embodiment, an additional layer of porous electronically-conductive
5   material may be positioned between two outer layers of porous electronically-conductive material. A solid layer of polymeric material is positioned between the center porous layer and each outer layer. The center layer is thicker and selected so that it does not compress as easily as the outer layers of porous material during the fabrication process. The thicknesses of the center layers and the solid layers of polymeric material are selected so
10   that the center layer does not become completely filled with polymeric material during the molding process. This type of bipolar plate configuration leaves an open porous area in the middle of the bipolar plate, through which a cooling fluid may be circulated.

The following examples illustrate the invention, but are not intended to limit it in any way. Unless otherwise stated, all parts and percentages are given by weight.

15   <u>Example 1</u>

Three membrane and electrode assemblies ("MEAs") were prepared according to the method described in PCT publication No. WO 97/13287. The Pt catalyst loadings of the three cathode and three anode sides were 0.21, 0.19 and 0.18; and 0.14, 0.13, and 0.17 mg/cm^2, respectively. The active (catalyzed) area of each of the three cells was 19.8 cm^2.
20   The MEAs were soaked in dilute sulfuric acid, then water, and loaded into the stack wet.

Porous cathode flow fields were constructed according to the method described in PCT publication No. WO 97/13287. Porous carbon paper having a porosity of 90 percent and 24 mils thick (available as Spectracarb™ paper from Spectracorp (Lawrence, MA)) was made hydrophilic by oxidation in a medium comprising 0.006 M silver sulfate, 0.2 M sodium
25   persulfate and 0.5 M sulfuric acid at a temperature of 60°C for 1 hour. The porous anode flow fields were density 0.42 g/cm^3, 14-mil thick porous carbon paper, also from Spectracorp. The edges of the flow fields were sealed with epoxy to provide a gas tight seal both internally and to the exterior of the stack.

Air and hydrogen delivery layers were constructed from 3 layers of 10-mil thick Grafoil™ graphite paper by cutting out channels with a scalpel. When the stack was assembled, these layers cooperated with the bipolar plates and MEAs to form ducts that delivered reactant gases to the porous flow fields. These ducts were joined to internal

5   manifolds that were formed from holes in the various elements when the stack was assembled.

End plates were constructed of 1/2-inch thick aluminum. Next to each end plate was placed a 73-mil thick layer of 316 alloy stainless steel to prevent corrosion of the inside face of the end plate.

10   Bipolar plates were constructed according to the present invention for use in the stack. Carbon fiber-filled nylon 66 (50 percent carbon fiber loading by weight, density 1.38 g/cm^3, obtained from DSM Engineering Plastics) was first dried at 80°F for 16 hours in vacuum (29 mm Hg), then compression molded using a programmable compression molding machine. The desired amount of carbon fiber-filled nylon 66 (calculated as the

15   thickness times the length times the width of the chase, or mold, times the density of the carbon fiber-filled nylon 66) was placed in the chase, or mold, which was sandwiched between two Kapton™ slip sheets. This assembly was then further sandwiched between two thick smooth-finish metal sheets and placed in the compression-molding machine. After a 4-minute heat-soak stage wherein the mold platens of the compression mold were pre-

20   heated to 540°F, closed, and compressed to a pressure of slightly above 0 psi, the pressure in the mold was increased to 500 lb for 4 minutes, and then increased to 10,000 lbf for 3 minutes, while maintaining the mold temperature at 540°F.

Spectracarb™ paper having a density of 0.50 g/cm^3 and a thickness of 11.5 mils was placed on both sides of the carbon fiber-filled nylon 66 molded layer. This arrangement was

25   placed in a 16-mil thick chase (mold) and returned to the compression-molding machine. Molding cycles identical to those described above were applied, giving a final fabricated product 16 mils thick. This product was tested for electrical resistivity and gas permeability before use as a bipolar plate material in the stack.

The stack was assembled from the cathode end plate up, using 1/8-inch diameter

30   nylon 66 rods as guides to align the stack elements. These guides were left in place in the

assembled stack. The order of stacking elements was as follows: aluminum anode end plate; stainless steel layer, hydrogen delivery layer, anode flow field; MEA 1; cathode flow field; air delivery layer; bipolar plate; hydrogen delivery layer; anode flow field; MEA 2; cathode flow field; air delivery layer; bipolar plate; hydrogen delivery layer; anode flow field;

5   MEA 3; cathode flow field; air delivery layer; stainless steel layer; and aluminum cathode end plate.

Once assembly was complete, the bolts were evenly tightened to 50 inch-pounds torque. The bolts were to be re-tightened over a period of hours to obtain uniform compression. Further tightening was required as the stack was heated to the operating

10   temperature of 80°C. The operational thickness of this stack under full compression (minus the end plates and stainless steel layers) was about 299 mils.

The stack was evaluated using a fuel cell test stand manufactured by Fuel Cell Technologies, Inc. (Los Alamos, NM). The test stand incorporated a 120 ampere Hewlett-Packard 60504B Electronic Load module with a 600 watt rating, as well as hardware to

15   provide flow control of gas streams, heating and humidity for both cathode and anode gases, and back-pressure control for operation at pressures above atmospheric pressure. During operation, the stack self-heated to above the desired operating temperature of 80°C, but adequate cooling was provided by an external fan.

The stack was operated under the following conditions: cathode gas: air at 30 psig

20   outlet pressure, 1970 standard cubic centimeters per minute (sccm) flow rate, and humidified at 88°C; and anode gas: hydrogen at 20 psig outlet pressure, 830 sccm flow rate, and humidified at 100°C. After a 24-hour break-in period, the stack delivered 1.70 volts at 19.8 A (1 A/cm^2), or about 34 watts.

Figure 4 is an exploded schematic diagram of stack based on porous flow fields and

25   containing the bipolar plate material of the present invention. From left to right, the elements are: end plate, air delivery layer, cathode flow field, MEA, anode flow field, hydrogen delivery layer, and bipolar plate.

Figure 5 shows selected stack components, as follows: (a) air delivery layer; (b) air flow field; (c) hydrogen delivery layer; and (d) hydrogen flow field.

Examples 2-7

     Carbon-containing solid layers were prepared using the method described in Example 1, using the following materials and molding parameters:

Table 1. Carbon-filled Thermoplastics

Carbon filler	Load (% wt.)	Plastic	Form, density (g/cm^3)	Company, material code	Drying Vacuum Conditions	Melting Temp. (°F)
Black	40	poly-propylene	pellets, 0.97-1.01	RTP Co., ESD-C-100	no	450
Fiber	40	poly-carbonate	pellets, 1.36	RTP Co., RTP-387	110°C, 16 hrs., 29 mm Hg Vac	610
Fiber	50	nylon 66	pellets, 1.38	DSM Eng. Plastics, J-1/CF/50/EG	80°F, 16 hrs., 29 mm Hg Vac	540

Table 2. Materials and Molding Conditions

Molding Stages		Material		
		PP & Carbon Black	PC & Carbon Fiber	Nylon 66 & Carbon Fiber
Temperature (°F)		450	610	540
Stage 1	Heat Soak (minutes)	3	3	4
Stage 2	Time (minutes)	5	10	4
	Low-Pressure (lbf)	500	500	500
Stage 3	Time (minutes)	3	3	3
	High-Pressure (lbf)	10000	10000	10000
Time to cool mold to ambient temperature using a heat-transfer fluid (minutes)		20	20	20

Notes: The chase (mold) is 8-mils thick, 5.75 in. long, and 5.75 in. wide.

5   PP = polypropylene; PC = polycarbonate.

Bipolar plates were then prepared using the above-described solid layers and the following carbon papers. The carbon papers were obtained from Spectracorp (Lawrence, MA) and Toray (Tokyo, Japan). In Comparative Examples 1 and 2, the carbon paper/plastic assemblies were compressed sufficiently to cause the fibers of the paper to touch each other within the bipolar plate, in order to achieve electrical contact between the layers and good conductivity.

Table 3. Bipolar Plate Compositions

Example No.	Carbon paper, density (g/cm³), thickness (mil)	Fill	Plastic	Plate Thickness (mil)
Comp. Ex. 1 *	Spectracorp, 0.50, 11.5	none	nylon 66	21.5
2	Toray (TGPH090), 0.50, 9	carbon fiber	nylon 66	23
3**	Spectracorp, 0.50, 11.5	carbon fiber	nylon 66	16
4	Spectracorp, 0.50, 11.5	carbon black	polypropylene	20
5	Spectracorp, 0.25, 8	carbon fiber	nylon 66	12
Comp. Ex. 2 *	Spectracorp, 0.50, 11.5	none	polypropylene	19.5
6	Spectracorp, 0.69, 18.5	carbon fiber	nylon 66	44.5
7	Spectracorp, 0.67, 11.5	carbon fiber	nylon 66	32.5

* Comparative Example - not an example of the invention.

Below are the values for the product of through-plane resistivity for Examples 2-7.

Table 4

Example No.	Area Resistivity (Ω-cm²)	Permeability (μD)
Comp. Ex. 1*	0.0202	too high to measure
2	0.00018	0.14
3	0.0018	0.20
4	0.0042	2.5
5	0.00024	3.7
Comp. Ex. 2*	0.00074	15
6	0.0068	2.1
7	0.014	1.2

Examples 8-10

5   Three bipolar plates with cooling channels were assembled as illustrated in Figure 3, using polytetrafluoroethylene or steel tubing as a conduit material, except that carbon paper is used in Example 8. The chase (mold) thickness (See Figure 3) was double the plate thickness. The carbon paper used was 11.5 mils thick and had a density of 0.50 g/cm^3. The assemblies were molded under the conditions described in Examples 1-7.

10   Table 5. Dimensions of Components for the Bipolar Plate with Cooling Channels

Example No.	Material	Conduit Diameter	Plate Thickness (mil)
8	carbon black & polypropylene	1/16 in. polytetrafluoroethylene	63
9	carbon fiber & nylon 66	1/16 in. polytetrafluoroethylene	63
10	carbon fiber & nylon 66	18 gauge stainless steel	42

        Upon molding, the polytetrafluoroethylene tubing did not collapse when placed in between the carbon black-polypropylene plates and was easily retrieved. The cooling holes that ran inside the plate were centered. The carbon-black polypropylene had a relatively

15 low viscosity at its processing temperatures, and the molten material easily conformed around the polytetrafluoroethylene tubing. However, due to the much greater viscosity of the carbon fiber-filled nylon 66 at its recommended processing temperature, the polytetrafluoroethylene tubing collapsed when trying to mold a plate out of this material.

        When the stainless steel conduit, gauge 18, was employed to mold cooling channels

20 in a carbon-fiber nylon 66 bipolar plate, the tubing did not collapse. The metal tubing was not retrieved.

CLAIMS:

1. A bipolar separator plate for two electrochemical cells connected in series, the plate comprising two layers of a porous electronically-conductive material having positioned therebetween a solid layer of a polymeric material having dispersed therein at least 1 percent by weight of a conductive filler, wherein the plate has an area resistivity of less than 1 ohm-cm^2, and wherein the solid layer has a permeability of less than 50 μDarcy (μD).

2. The separator plate of claim 1 wherein the conductive filler is used in an amount, based on the weight of the polymeric material, of at least 20 percent.

3. The separator plate of claim 1 wherein the conductive filler is used in an amount, based on the weight of the polymeric material, of at least 50 percent.

4. The separator plate of claim 1 wherein the conductive filler is carbon fiber having a diameter of 7 μm.

5. The separator plate of claim 1 which has a thickness of at least 10 mils.

6. The separator plate of claim 1 wherein the porous electronically-conductive material is carbon fiber paper having a porosity of at least 60 percent.

7. The separator plate of claim 1 wherein the polymeric material is a thermoplastic polyurethane.

8. The separator plate of claim 1 wherein the polymeric material is a polypropylene.

9. The separator plate of claim 1 wherein the polymeric material is a syndiotactic polystyrene.

10. The separator plate of claim 1 wherein the polymeric material is a vinyl ester resin.

11. The separator plate of claim 1 wherein the polymeric material is polyvinylidene fluoride.

12. The separator plate of claim 1 wherein the polymeric material is polytetrafluoroethylene.

13. The separator plate of claim 1 wherein the polymeric material is a polyepoxide.

14. A bipolar separator plate for two electrochemical cells connected in series, the plate comprising three layers of a porous electronically-conductive material having positioned between the first and second layer, and the second and third payer, a solid layer

5 of a polymeric material having dispersed therein at least 1 percent by weight of a conductive filler, wherein the plate has an area resistivity of less than 1 ohm-cm^2, and wherein the solid layer has a permeability of less than 50 µDarcy (µD).

15. An electrochemical device having at least two electrochemical cells connected in series, each cell containing a gas or liquid material which is separated from a different

10 gas or liquid material in an adjacent cell by two porous layers of electronically-conductive material having positioned therebetween a solid layer of a polymeric material having dispersed therein at least 1 percent by weight of a conductive filler, wherein the plate has an area resistivity of less than 1 ohm-cm^2, and wherein the solid layer has a permeability of less than 50 µD.

15 16. The electrochemical device of claim 15 wherein the conductive filler is used in an amount, based on the weight of the polymeric material, of at least 50 percent.

17. The electrochemical device of claim 15 wherein the conductive filler is carbon fiber having a diameter of 7 µm.

18. The electrochemical device of claim 15 which has a thickness of at least 20 mils.

20 19. The electrochemical device of claim 15 wherein the porous electronically-conductive material is a carbon fiber paper having a porosity of at least 70 percent.

Fig. 1

Figure 2:

Carbon Paper Impregnated with
Plastics and Carbon Reinforcement

Carbon-Reinforced
Plastics

Cooling Channels

Figure 3:

Carbon Paper Layer

Carbon Reinforced Thermoplastics Plate

Tubing

Locating Plate
(one on each side)

Carbon Reinforced Thermoplastics Plate

Carbon Paper Layer

Chase (Mold)

Figure 4:

repeating unit

end plate   air delivery layer   cathode flowfield   MEA   anode flowfield   H2 delivery layer   bipolar plate

Figure 5:

INTERNATIONAL SEARCH REPORT

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6   H01M8/02   C25B9/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6   H01M   C25B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 505 992 A (DETTLING CHARLES J ET AL) 19 March 1985 (1985-03-19) cited in the application column 7, line 61 - column 8, line 68 figures 4,5 ---	1-19
A	EP 0 784 352 A (NISSHIN SPINNING) 16 July 1997 (1997-07-16) page 2, line 41-53 ---	1-19
A	US 4 579 789 A (FUKUDA HIROYUKI ET AL) 1 April 1986 (1986-04-01) column 2, line 55-59 column 3, line 9-20 column 5, line 34-42 ---	1-19

-/--

[X] Further documents are listed in the continuation of box C.   [X] Patent family members are listed in annex.

° Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
6 August 1999	23/08/1999

Name and mailing address of the ISA	Authorized officer
European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Engl, H

Form PCT/ISA/210 (second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication,where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 012, no. 069 (E-587), 3 March 1988 (1988-03-03) & JP 62 211868 A (FUJI ELECTRIC CO LTD), 17 September 1987 (1987-09-17) abstract ---	1-19
P,A	WO 98 33221 A (LYNNTECH INC) 30 July 1998 (1998-07-30) page 3, line 4-8 page 7, line 15-27 -----	1-19

1

INTERNATIONAL SEARCH REPORT

Information on patent family members

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
US 4505992	A	19-03-1985	AT	46593 T	15-10-1989
			CA	1227529 A	29-09-1987
			EP	0122150 A	17-10-1984
			JP	1843019 C	12-05-1994
			JP	5052037 B	04-08-1993
			JP	60023975 A	06-02-1985
			US	4732637 A	22-03-1988
EP 0784352	A	16-07-1997	CA	2198496 A	23-01-1997
			WO	9702612 A	23-01-1997
US 4579789	A	01-04-1986	JP	1695356 C	17-09-1992
			JP	3063183 B	30-09-1991
			JP	60236460 A	25-11-1985
			JP	61019071 A	27-01-1986
			JP	1892875 C	26-12-1994
			JP	6022137 B	23-03-1994
			JP	61019069 A	27-01-1986
			CA	1259101 A	05-09-1989
			DE	3512866 A	24-10-1985
			FR	2562718 A	11-10-1985
			GB	2157482 A,B	23-10-1985
			US	4855092 A	08-08-1989
JP 62211868	A	17-09-1987	NONE		
WO 9833221	A	30-07-1998	AU	6648198 A	18-08-1998